

# UNCLASSIFIED

AD NUMBER	
AD036975	
CLASSIFICATION CHANGES	
TO:	unclassified
FROM:	confidential
LIMITATION CHANGES	
TO: Approved for public release; distribution is unlimited.	
FROM: Distribution authorized to U.S. Gov't. agencies and their contractors; Administrative/Operational Use; 16 APR 1954. Other requests shall be referred to Material Lab., New York Naval Shipyard, Brooklyn.	
AUTHORITY	
DNA ltr, 15 Mar 1977; DNA ltr, 15 Mar 1977	

THIS PAGE IS UNCLASSIFIED

AFSWP-397

Lab. Project 5046-3, Part 55  
Final Report  
NS 081-001

AD 10.8819.75  
ASTIA FILE COPY



**MATERIAL LABORATORY**  
**NEW YORK NAVAL SHIPYARD**  
**BROOKLYN 1, N. Y.**

**TECHNICAL REPORT**

NYNS 504

PROPERTY OF R.D.  
TECHNICAL LIBRARY

3ND-NYNS-200.10



3ND-PSPC-2430

SECURITY INFORMATION

54AA-31900

**NOTICE: THIS DOCUMENT CONTAINS INFORMATION AFFECTING THE  
NATIONAL DEFENSE OF THE UNITED STATES WITHIN THE MEANING  
OF THE ESPIONAGE LAWS, TITLE 18, U.S.C., SECTIONS 793 and 794.  
THE TRANSMISSION OR THE REVELATION OF ITS CONTENTS IN  
ANY MANNER TO AN UNAUTHORIZED PERSON IS PROHIBITED BY LAW.**

THIS REPORT HAS BEEN DELIMITED  
AND CLEARED FOR PUBLIC RELEASE  
UNDER DOD DIRECTIVE 5200.20 AND  
NO RESTRICTIONS ARE IMPOSED UPON  
ITS USE AND DISCLOSURE.

DISTRIBUTION STATEMENT A

APPROVED FOR PUBLIC RELEASE;  
DISTRIBUTION UNLIMITED.

CONFIDENTIAL

CRITICAL THERMAL ENERGIES  
of  
CANOPY MATERIALS

Submitted by  
THE WRIGHT AIR DEVELOPMENT CENTER  
Department of the Air Force

L. Banet  
J. Bracciaventi

Lab. Project 5046-3, Part 55  
Final Report  
NS 081-001  
Technical Objective AW-7  
AFSWP-397

16 April 1954

Optics and Nucleonics Branch  
J. M. McGREEVY, Head

Superintending Engineer  
O. J. DASHEFSKY

The Director  
CAPT. A. B. JONES, Jr., USN

MATERIAL LABORATORY  
New York Naval Shipyard  
Brooklyn 1, New York

CONFIDENTIAL

Lab. Project 5046-3, Part 55  
Final Report

ABSTRACT

For the purpose of evaluating the resistance of materials to the thermal radiation of atomic explosions, the critical thermal energies and the apparent transmissions of six canopy materials were determined. The materials were evaluated by exposure to the Material Laboratory carbon-arc source of thermal radiation and examination of the consequent damage to the cloths. The amount of radiation transferred through the materials was determined by using black carbon paper, mounted with a 1/16-inch air gap behind the cloths. The methods of exposing the materials to determine initial energies and of measuring the apparent transmissions are indicated. It was found that initial effects, whenever observed, occurred between 7.2 and 27 cal/cm<sup>2</sup>. Destruction of the cloths occurred at values ranging from 32 to 50 cal/cm<sup>2</sup>, depending upon the material employed. Apparent transmittance values of less than 3 per cent were found on the two aluminized cotton materials and the butyl coated cotton sateen and the highest transmittance (9 per cent) on the white cotton sateen.

CONFIDENTIAL

Lab. Project 5046-3, Part 55  
Final Report

CONTENTS

	<u>Paragraph No.</u>
AUTHORITY	1
INTRODUCTION	2
EQUIPMENT AND METHODS	4
RESULTS	6
CONCLUSIONS	9
BIBLIOGRAPHY	

CONFIDENTIAL

Lab. Project 5046-3, Part 55  
Final Report

Ref: (a) COMNAVSHIPYDNYK conf ltr S99/L5 Ser 960-92 of 14 Mar 1950  
(b) BUSHIPS spdltr S99(9)(348) Ser 348-75 of 6 Apr 1950

Encl: (1) Critical Thermal Energies of Canopy Materials  
(2) Apparent Transmission of Canopy Materials

AUTHORITY

1. This investigation is part of the program proposed by reference (a) and formally approved by reference (b). The investigation of the canopy materials was requested by the Wright Air Development Center. The general Thermal Radiation Program is under the supervision of the Armed Forces Special Weapons Project.

INTRODUCTION

2. As part of its general program on the effects of the thermal radiation of atomic explosions, the Naval Material Laboratory is evaluating the characteristics, under exposure to intense thermal radiation, of the various materials of particular interest to the several agencies of the Department of Defense. As data become available, these findings are published.

3. The six canopy fabrics were submitted to the Material Laboratory by C. A. Willis, Uniform Textile Section (WCRTT-2), Wright Air Development Center, on 12 January 1954.

EQUIPMENT AND METHODS

4. The critical thermal energies of the canopy materials were determined, employing the Naval Material Laboratory carbon-arc source of thermal radiation. The source consists of an 11-mm carbon arc, mounted at the focus of a reflector which collimates the emitted energy. A second mirror, which is mounted coaxially at a distance of twelve feet from the collimator, condenses the radiation to the mirror's focus. Gradations of thermal damage are obtained by varying the effective exposure time through accelerating a 1 x 8-inch specimen transversely through the focus. The carbon arc furnishes an irradiance of 85 cal/cm<sup>2</sup>sec over a central area, 2-mm in width. For a better approximation of the laboratory exposure time to those associated with the radiation of a nominal atomic bomb, attenuating screens were employed. Exposure times between 0.3 and 0.6 seconds were employed for radiant exposures up to 53 cal/cm<sup>2</sup>.



CONFIDENTIAL

Lab. Project 5046-3, Part 55  
Final Report

5. For the exposure, the fabrics were cut into 1x8-inch specimens and mounted 1/16-inch above a black, heat-sensitive carbon paper, fastened on glass melamine blocks which were provided with cut-outs to furnish an air background behind the paper. Using attenuating screens, the exposures were increased up to a value of 50 cal/cm<sup>2</sup>, and a glass silicone mask with several stops was employed to reduce flame propagation during exposure. Placing black carbon paper under the cloths and examining the resulting damage of the paper, an estimate of the radiation transmittance was obtained from the ratio of the exposure values required to produce certain effects on the paper to the total exposure values required to produce the effects directly.

RESULTS

6. The critical thermal energies of the canopy materials, submitted by the Wright Air Development Center, were defined as those which produce certain characteristic reproducible effects on the materials, such as charring or destruction. The measured critical energies are given in Enclosure (1).

7. It may be noted that the laboratory exposures have been made under highly controlled conditions and, as a rule, give results which can be reproduced very well. However, for several reasons, the data of Enclosure (1) should be used with caution. The effects to be observed on material surfaces remain unchanged over a considerable range of exposures. Since the surface effects are not sufficiently gradated for refined evaluations, only the initial stages have been recorded. The effects are influenced by such factors as mounting, geometry of material and of exposure, weathering and moisture content at the time of exposure. Differences in density, absorptivity, chemical composition, weave, and surface structure are responsible for the varying effects which may be observed from area to area on the same material. Liquids and gases form during exposure to thermal radiation, even in a period of less than one second, thereby affecting the amount of thermal radiation, incident on and absorbed by the surface. A review of the critical energy values shows the following:

- (a) Except for flaming or total destruction, the first effects observed on the cloths occurred at radiant exposures of from 7.2 to 27 cal/cm<sup>2</sup>.
- (b) Of the six materials, the aluminized cotton showed the earliest effects, at 7.2 cal/cm<sup>2</sup>.

CONFIDENTIAL

Lab. Project 5046-3, Part 55  
Final Report

- (c) The most resistant of the materials were the white cotton sateen (9 oz/yd<sup>2</sup>) and the silicone rubber coated glass fabric, which were not affected under radiant exposures up to 41 cal/cm<sup>2</sup>.
- (d) All of the materials flamed during exposure. The new aluminized cotton flamed at the lowest exposure values of 21 cal/cm<sup>2</sup> and the silicone rubber coated glass fabric, cotton sateen and cotton duck at 41 cal/cm<sup>2</sup>, the highest value for this damage.
- (e) The least resistant to destruction is the butyl rubber coated cotton sateen which was consumed at 32 cal/cm<sup>2</sup>.

8. The apparent transmittance values of the fabrics, determined by the effects on the carbon paper, are shown on Enclosure (2). The two aluminized cotton materials and the butyl coated cotton sateen have transmittance values of less than 1 per cent below exposures of 9 cal/cm<sup>2</sup>. For exposures up to 25 cal/cm<sup>2</sup>, these three materials have apparent transmittance values of less than 3.1 per cent. The remaining three materials transmit considerably more; the cotton sateen indicated the highest transmission value, approximately 9 per cent.

CONCLUSIONS

9. The results of this investigation are summarized as follows:

- (a) Initial effects of the canopy materials occur after exposures ranging from 7.2 to 27 cal/cm<sup>2</sup>.
- (b) The materials flame during exposure at values ranging from 21 to 41 cal/cm<sup>2</sup>.
- (c) Butyle rubber coated sateen, cotton sateen, cotton duck and silicone rubber coated glass fabrics are progressively more resistant to destruction.
- (d) The apparent transmittances of the aluminized cotton materials and the butyl coated cotton sateen are the lowest, that of the cotton sateen is the largest (approximately 9 per cent).

Approved:

  
B. JONES, JR., CAPTAIN, USN  
The Director

CONFIDENTIAL

Lab. Project 5046-3, Part 55  
Final Report

#### BIBLIOGRAPHY

1. Material Laboratory, New York Naval Shipyard. Critical Thermal Energies of Clothing Materials Submitted by the U.S. Marine Corps, Report No. 5046-3, Part 3 (July 1951).
2. Material Laboratory, New York Naval Shipyard. Critical Thermal Energies of Special Awning Materials, Submitted by the Bureau of Ships, Department of the Navy, Report No. 5046-3, Part 27 (Jan 1953).
3. Material Laboratory, New York Naval Shipyard. Determination of Energy Distribution at the Focus of a Parabolic Mirror and the Energy Density on a Moving Surface, Using a Tungsten Lamp Source, Report No. 5046, Part 5 (July 1949).
4. Material Laboratory, New York Naval Shipyard. A Method of Measuring High Intensities at the Focus of a Parabolic Reflector with Large Relative Aperture, Report No. 5046, Part 3 (November 1948).

CONFIDENTIAL

Material Laboratory

Lab. Project 504643, Pt. 55  
Final Report  
Enclosure (1)

Critical Thermal Energies  
of  
Canopy Materials

Submitted by the Wright Air Development Center

Department of the Air Force

MATERIAL	DESCRIPTION OF EFFECT	CRITICAL ENERGY (cal/cm <sup>2</sup> )
Cotton, Aluminized Type I, new	Aluminum dulls	8.2
	Surface chars	18
	Flames during exposure	21
	Cotton chars through	31
	Destroyed by afterflame and afterglow	42
Cotton, Aluminized Type I, previously used in aircraft	Aluminum dulls	7.2
	Surface chars	9.5
	Cotton chars through	19
	Flames during exposure	24
	Destroyed by afterflame and afterglow	34
Cotton, Sateen, white, 9 oz/sq.yd., Mil-C-557	Destroyed by afterflame and afterglow	41-50
Butyl Rubber Coated Cotton Sateen	Surface chars	22
	Destroyed by afterflame	32
Bleached Cotton Duck 14.7 oz/sq.yd.	Chars sporadically	27
	Destroyed by afterflame and afterglow	41-50
Silicone Rubber Coated Glass Fabric	Flames during exposure and forms powdered ash	41

CONFIDENTIAL

CONFIDENTIAL

Material Laboratory

Lab. Project 5046-3, Pt. 55  
Final Report  
Enclosure (2)

Apparent Transmission  
of  
Canopy Materials

Submitted by the Wright Air Development Center

Department of the Air Force

MATERIAL	EXPOSURE ON CLOTH (cal/cm <sup>2</sup> )	APPARENT TRANSMISSION	
		Indicated Effect (cal/cm <sup>2</sup> )	Per cent
Cotton, Aluminized Mil-C-7646, Type (New)	8.8	0.059	0.67
	25	<0.78	<3.1
Cotton, Aluminized, Mil-C-7646, previously used in aircraft	8.6	0.059	0.69
	25.0	<0.78	<3.1
Cotton Sateen, white 9 oz/sq.yd., Mil-C-557	0.61	0.059	9.7
	9.3	0.78	8.4
Butyl Rubber Coated Cotton Sateen	11	0.059	0.53
	25	<0.78	<3.1
Bleached Cotton Duck 14.7 oz/sq.yd.	16	0.78	4.9
Silicone Rubber Coated Glass Fabric	0.91	0.059	6.9
	12	0.78	6.5

CONFIDENTIAL

DISTRIBUTION LIST  
No. 100  
Thermal Radiation Reports  
(Research)

8 December 1953  
No. of Cys

<u>ADDRESSEE</u>	<u>ARMY</u>	
Asst Chief of Staff, G-3, D/A, Washington 25, D.C. ATTN: DCS/G-3 (RR&SW)		1
Asst Chief of Staff, G-4, D/A, Washington 25, D.C.		1
Chief of Ordnance, D/A, Washington 25, D.C., ATTN: ORDTX-AR		1
Chief Signal Officer, D/A, P&O Div, Washington 25, D.C. ATTN: SIGOP		3
The Surgeon General, D/A, Washington 25, D.C., ATTN: Chairman, Med R&D Board		1
Chief Chemical Officer, D/A, Washington 25, D.C.		2
Office of the Chief of Engineers, Washington 25, D.C. ATTN: ENGNB		3
The Quartermaster General, CBR, Liaison Office, R&D Div, D/A, Washington 25, D.C.		2
Chief of Transportation, Military Planning & Intelligence Div, Washington 25, D.C.		1
Chief, Army Field Forces, Ft Monroe, Va.		4
President, Board #1, OCAFF, Ft Bragg, NC		1
President, Board #4, OCAFF, Ft Bliss, Texas		1
Commander-in-Chief, FECOM, APO 500, c/o PM San Francisco, Calif. ATTN: ACOFS J-3		2
Commandant, Command & General Staff College, Ft Leavenworth, Kansas ATTN: ALLIS (AS)		1
Commanding General, Medical Field Service School, Brooke Army Medical Center, Ft. San Houston, Texas		1
Director, Special Weapons Development Office, OCAFF, Ft Bliss, Tex		1
Commandant, Army Medical Service Graduate School, Walter Reed Army Medical Center, Washington 25, D.C., ATTN: Dept of Biophysics		1
Commandant, Chemical Corps School, Chemical Corps Training Command, Ft McClellan, Ala.		1

## DISTRIBUTION LIST NO. 100 (CONT)

<u>ADDRESSEE</u>	<u>ARMY</u>	<u>No. of Cys</u>
Commanding General, Research & Engineering Command, Army Chemical Center, Md., ATTN: Special Projects Officer		2
RD Control Officer, Aberdeen Proving Grounds, Md., ATTN: Director Ballistics Research Laboratory		2
Commanding General, The Engineer Center, Ft Belvoir, Va., ATTN: Asst.Commandant, Eng School		3
Commanding Officer, Engineer Research & Development Laboratory, Ft. Belvoir, Va., ATTN: Chief, Tech Intelligence Branch		1
Commanding Officer, Picatinny Arsenal, Dover, New Jersey, ATTN: ORDBB-TK		1
Commanding Officer, Frankford Arsenal, Philadelphia 37, Pa., ATTN: RD Control Officer		1
Commanding Officer, Army Medical Research Laboratory, Ft Knox, Ky.		1
Commanding Officer, Chemical Corps Chemical & Radiological Lab., Army Chemical Center, Md., ATTN: Tech Library		2
Commanding Officer, Transportation R&D Station, Ft Eustis, Va.		1
Director, Technical Documents Center, Evans Signal Laboratory, Belmar, N.J.		1
Director, Waterways Experiment Station, PO Box 631, Vicksburg, Miss. ATTN: Library		1
Director, Operations Research Office, Johns Hopkins University, 6410 Connecticut Ave., Chevy Chase, Md., ATTN: Library		1
Chief, QM R&D Lab., Philadelphia QM Depot, 2800 S. 20th St., Philadelphia 45, Pa., ATTN: Mr. John Davies		1

NAVY

Chief of Naval Operations, D/N, Washington 25, D.C., ATTN: OP-36	1
Chief of Naval Operations, D/N, Washington 25, D.C., ATTN: OP-374(OEG)	1
Chief, Bureau of Medicine and Surgery, D/N, Washington 25, D.C., ATTN: Special Weapons Defense Division	1
Chief, Bureau of Ordnance, D/N, Washington 25, D.C.	1
Chief of Naval Personnel, D/N, Washington 25, D.C. ATTN: Pers C	1
Chief, Bureau of Ships, D/N, Washington 25, D.C. ATTN: Code 348	2

## DISTRIBUTION LIST NO. 100 (CONT)

ADDRESSEE	NAVY	No. of Cys
Chief, Bureau of Supplies & Accounts, D/N, Washington 25, D.C.		1
Chief, Bureau of Yards & Docks, D/N, Washington 25, D.C. ATTN: P-312		1
Chief, Bureau of Aeronautics, D/N, Washington 25, D.C.		2
Chief of Naval Research, Code 219, Rm 1807, Bldg T-3, Washington 25, D.C., ATTN: RD Control Officer		1
Commander-in-Chief, US Pacific Fleet, Fleet Post Office, San Francisco, California		1
Commander-in-Chief, US Atlantic Fleet, US Naval Base, Norfolk 11, Va		1
Commandant, United States Marine Corps, Washington 25, D.C. ATTN: CodeAO3H		4
President, US Naval War College, Newport, Rhode Island		1
Superintendent, US Naval Postgraduate School, Monterey, Calif		1
Commanding Officer, US Naval Schools Command, US Naval Station Treasure Island, San Francisco, Calif		2
Commanding Officer, US Fleet Training Center, Naval Base, Norfolk 11, Va. ATTN: Special Weapons School		2
Commanding Officer, US Fleet Training Center, Naval Station, San Diego 36, Calif, ATTN: (SPWP School)		2
Commanding Officer, Air Development Squadron 5, VX-5, US Naval Air Station, Moffett Field, Calif		1
Commanding Officer, US Naval Damage Control Training Center, Naval Base, Philadelphia 12, Pa., ATTN: ABC Defense Course		1
Commanding Officer, US Naval Unit, Chemical Corps School, Army Chemical Training Center, Ft McClellan, Ala		1
Commander, US Naval Ordnance Laboratory, White Oak, Md, Silver Spring 19, Md., ATTN: EE R		1 1
Commander, US Naval Ordnance Test Station, Inyokern, China Lake, Calif		1
Commanding Officer, US Naval Medical Research Institute, National Naval Medical Center, Bethesda 14, Md.		1
Director, US Naval Research Laboratory, Washington 25, D.C.		1



## DISTRIBUTION LIST NO. 100 (CONT)

ADDRESSEENAVYNo. of Cys

Director, The Material Laboratory, New York Naval Shipyard,  
Brooklyn, New York

1

Commanding Officer, & Director, US Naval Electronics Lab.,  
San Diego, Calif, ATTN: Code 4223

1

Commanding Officer, US Naval Radiological Defense Laboratory,  
San Francisco 24, Calif., ATTN: Tech. Info Div

3

Commander, US Naval Air Development Center, Johnsville, Pa

1

Director, Office of Naval Research Branch Office, 1000 Geary St.,  
San Francisco, California

2

Officer-in-Charge, US Naval Clothing Factory, US Naval Supply Activities  
New York, 3rd Ave., & 29th St., Brooklyn 32, N.Y. ATTN: R&D Div

1

Commanding Officer, Naval Medical Field Research Laboratory, Camp Lejeune, NC

1

AIR FORCE

Asst for Atomic Energy, Hqs, USAF, Washington 25, D.C. ATTN: DCS/O

1

Director of Operations, Hqs, USAF, Washington 25, D.C. ATTN: Operations  
Analysis

1

Director of Plans, Hqs, USAF, Washington 25, D.C. ATTN: War Plans

1

Directorate of Requirements, Hqs, USAF, Washington 25, D.C. ATTN: AFDRQ-SA/M

1

Directorate of Research & Development, Armament Division, DCS/D, Hqs,  
USAF, Washington 25, D.C.

1

Directorate of Intelligence, Hqs, USAF, Washington 25, D.C. ATTN: AFOIN-1B2

2

The Surgeon General, Hqs, USAF, Washington 25, D.C. ATTN: Bio. Def. Br.,  
Pre. Med. Div.

1

Commander, Strategic Air Command, Offutt AFB, Omaha Neb, ATTN: Chief  
Operations Analysis

1

Commander, Tactical Air Command, Langley AFB, Va., ATTN: Doc Sec Br

1

Commander, Air Defense Command, Ent AFB, Colorado

1

Commander, Air Materiel Command, Wright-Patterson AFB, Dayton, Ohio,  
ATTNF MCAIDS

2

DISTRIBUTION LIST NO. 100 (CONT)

<u>ADDRESSEE</u>	<u>AIR FORCE</u>	<u>No. of Cys.</u>
Commander, Air Training Command, Scott AFB, Belleville, Ill. ATTN: DCS/O GTP		1
Commander, Air Research & Development Command, PO Box 1395, Baltimore, Md., ATTN: RDDN		3
Commander, Air Proving Ground Command, Eglin AFB, Fla., ATTN: AG/TRB		1
Commander, Air University, Maxwell AFB, Alabama		2
Commander, Flying Training Air Force, Waco, Texas, ATTN: Dir of Observer Training		2
Commander, Crew Training Air Force, Randolph AFB, Randolph Field, Texas, ATTN: 2GTS, DCS/O		1
Commander, Headquarters Technical Training Air Force, Gulfport, Miss. ATTN: TA & D		1
Commander, Air Force School of Aviation Medicine, Randolph AFB, Tex		2
Commander, Wright Air Development Center, Wright-Patterson AFB, Dayton, Ohio, ATTN: WCOESP		1
Commander, AF Cambridge Research Center, 230 Albany Street, Cambridge 39, Mass., ATTN: Atomic Warfare Directorate		1
CRHK, Geophysics Research Directorate		1
Commander, AF Special Weapons Center, Kirtland AFB, N.M. ATTN: Tech Library		3
Commander, USAF Institute of Technology, Wright-Patterson AFB, Dayton, Ohio ATTN: Resident College		1
Commander, Lowry AFB, Denver, Colo. ATTN: Dept of Armament Tng.		1

OTHER DOD ACTIVITIES

Director, Weapons Systems Evaluation Group, OSD, Rm 2E1006, Pentagon, Washington 25, D.C.	1
United States National Military Representative, Headquarters, SHAPE, APO 55, c/o PM New York, N.Y. ATTN: Col. J.P. Healy	1
Asst. Secretary of Defense for Research and Development, DOD, Washington 25, D.C. ATTN: Tech Library	1
Commandant, Armed Forces Staff College, Norfolk 11, Va. ATTN: Secy	1
Commanding General, Field Command, AFSWP, PO Box 5100, Albuquerque, N.M.	6

## DISTRIBUTION LIST NO. 100 (CONT)

ADDRESSEEOTHER DOD ACTIVITIESNo. of Cys.

Chief, AFSTT, PO Box 2610, Washington 13, D.C.

15

PANEL ON THERMAL RADIATION

Dr. H. C. Hottel, Mass. Institute of Technology, Cambridge, Mass.

1

Dr. E. O. Hulburt, Director Naval Research Laboratory, Washington 25, DC

1

Dr. H. E. Pearce, Strong Memorial Hospital, 260 Crittenden Blvd.,  
University of Rochester 7, N.Y.

1

Dr. J. D. Hardy, Aviation Medical Acceleration Laboratory, Naval  
Air Development Center, Johnsville, Pa.

1

OTHERS

Dr. E. F. Cox, Applied Physics Div, Sandia Corp, Albuquerque, N.M.

1

Dr. Alvin C. Graves, Los Alamos Scientific Lab. Box 1663, Los Alamos, N.M.

1

Director, Los Alamos Scientific Lab., PO Box 1663, Los Alamos, N.M.  
ATTN: Reports Library

1

Engineering Research, University of California, PO Box 4063, Westwood  
Village Station, Los Angeles 24, Calif,

1

Dr. William T. Ham Jr., Medical College of Virginia, Richmond, Va.

1

California Forest and Range Experimental Station, US Forest Service,  
PO Box 245, Berkeley, Calif. ATTN: W.L. Fons, Div Forest Fire Research

1

Prof. G.C. Williams, Dept. of Cml. Eng., Mass. Institute of Technology,  
Cambridge, Mass.

1

Mr. H. D. Bruce, Forest Products Lab., No. Walnut St., Madison 5, Wisc.

1

Mr. A.A. Brown, Chief, Fire Research Div., Forest Service, USDA,  
Washington 25, D.C.

1

Technical Operations Inc., 6 Schouler Court, Arlington 74, Mass.,  
ATTN: Dr. Frederick C. Henriques.

1